

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : A61L 27/00, A61F 2/28</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/39757 (43) International Publication Date: 12 August 1999 (12.08.99)</p>
<p>(21) International Application Number: PCT/US99/02560 (22) International Filing Date: 5 February 1999 (05.02.99) (30) Priority Data: 09/020,205 6 February 1998 (06.02.98) US (71) Applicant: OSTEOTECH, INC. [US/US]; 51 James Way, Eatontown, NJ 07724 (US). (72) Inventors: BOYCE, Todd, M.; 515 Wellington Place, Ab- erdeen, NJ 07747 (US). MANRIQUE, Albert; 8 Winthrop Drive, Manalapan, NJ 07726 (US). (74) Agents: DILWORTH, Peter, G. et al.; Dilworth & Barrese, 333 Earle Ovington Boulevard, Uniondale, NY 11553 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: OSTEOIMPLANT AND METHOD FOR ITS MANUFACTURE</p> <p>(57) Abstract</p> <p>The invention relates to an osteoimplant fabricated from a solid aggregate of bone derived elements possessing chemical linkages between their adjacent surface-exposed collagen. Also described are various other components which can be incorporated into the bone implant material such as bone-growth inducing substances; and a method of manufacture.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

OSTEOIMPLANT AND METHOD FOR ITS MANUFACTURE

BACKGROUND OF THE INVENTIONField of Invention

5 The present invention relates to an osteoimplant for
use in the repair, replacement and/or augmentation of
various portions of animal or human skeletal systems and
to a method for manufacturing the osteoimplant. More
particularly, this invention relates to an osteoimplant
made up of a solid aggregate of bone-derived elements
10 that are bonded to each other through chemical linkages
formed between their surface-exposed collagen.

Description of the Related Art

15 The use of autograft bone, allograft bone or
xenograft bone is well known in both human and veterinary
medicine. See Stevenson et al., *Clinical Orthopedics and
Related Research*, 323, pp. 66-74 (1996). In particular,
transplanted bone is known to provide support, promote
healing, fill bony cavities, separate bony elements such
as vertebral bodies, promote fusion and stabilize the
20 sites of fractures. More recently, processed bone has
been developed into shapes for use in new surgical
applications, or as new materials for implants that were
historically made of non-biologically derived materials.

SUBSTITUTE SHEET (RULE 26)

U.S. Patent No. 4,678,470 describes a non-layered bone grafting material produced from bone by a process which includes tanning with glutaraldehyde. The bone may be pulverized, used as a large block or machined into a precise shape. The tanning stabilizes the material and also renders it non-antigenic. The bone material may also be demineralized.

Collagen is a naturally occurring structural biomaterial and is a component of connective tissues, including bone, in all vertebrate species. Native collagen is a glycine-rich chain of amino acids arranged in a triple helix and can be crosslinked by a variety of procedures.

Tissue transglutaminase is described as being effective at increasing adhesive strength at a cartilage-cartilage interface. See Jurgensen, K., et al., *The Journal of Bone and Joint Surgery*, 79-A (2), 185-193 (1997).

U.S. Patent No. 5,507,813 describes a surgically implantable sheet formed from elongate bone particles, optionally demineralized, containing biocompatible ingredients, adhesives, fillers, plasticizers etc.

U.S. Patent No. 4,932,973 discloses an artificial organic bone matrix with holes or perforations extending into the organic bone matrix. The holes or perforations are indicated to be centers of cartilage and bone

induction following implantation of the bone matrix.

U.S. Patent No. 4,394,370 discloses a one-piece
sponge-like bone graft material fabricated from fully
demineralized bone powder or micro particulate bone, and
5 reconstituted collagen. The sponge-like graft is
optionally crosslinked with glutaraldehyde.

Another one-piece porous implant is described in
U.S. Patent No. 5,683,459. The implant is made up of a
biodegradable polymeric macrostructure, which is
10 structured as an interconnecting open cell meshwork, and
a biodegradable polymeric microstructure composed of
chemotactic ground substances such as hyaluronic acid.

SUMMARY OF THE INVENTION

The present invention provides an osteoimplant
15 which, due to chemical linkages formed between the
surface-exposed collagen of adjacent partially
demineralized bone elements from which the osteoimplant
is manufactured, exhibits good mechanical strength, is
biocompatible and, in a preferred embodiment, through its
20 bone healing activity and ability to contain bone-growth
inducing substances, can promote and/or accelerate new
bone growth.

It is therefore an object of the present invention
to provide an osteoimplant made up of a solid aggregate
25 of bone-derived elements, adjacent bone-derived elements

being bonded to each other through chemical linkages between their surface-exposed collagen, and which possesses good mechanical strength and biocompatibility.

5 It is another object of this invention to provide an osteoimplant which can optionally include another component such as a reinforcing particle or fiber, fillers, bone-growth inducing substances such as medically/surgically useful substances, and combinations thereof.

10 It is another object of the invention to provide an osteoimplant possessing a network of pores, perforations, apertures, channels or spaces which permits and encourages penetration by endogenous and exogenous bone healing materials and blood supply, and simultaneously
15 provides a means for incorporating one or more bone healing substances.

It is yet a further object of the present invention to provide an osteoimplant which can be fashioned into a variety of shapes and sizes which are not limited by
20 constraints imposed by the size and/or types of donor bone which are available for construction of the osteoimplant.

It is also an object of the invention to provide a method of manufacturing which will provide a strong,
25 biocompatible osteoimplant of any size and/or shape for implantation.

In keeping with these and other objects of the invention, there is provided an osteoimplant which comprises a solid aggregate of bone-derived elements with adjacent bone-derived elements being bonded to each other through chemical linkages between their surface-exposed collagen.

Further in keeping with the invention, there is provided a method for the manufacture of an osteoimplant which comprises providing a quantity of bone-derived elements presenting surface-exposed collagen and forming chemical linkages between the surface-exposed collagen to bond the elements into a solid aggregate.

The osteoimplant of the present invention possesses a significant advantage over the prior art in its ability to be biocompatible, non-antigenic and to provide good mechanical strength.

Another important advantage of the osteoimplant herein over prior art implants lies in its ability to function as a carrier for, and effectively diffuse, one or more bone-growth inducing substances that promote new bone growth and/or accelerate healing.

The term "osteogenic" as used herein shall be understood to refer to the ability of a substance to induce new bone formation via the participation of living cells from within the substance.

The term "osteoconductive" as used herein shall be understood to refer to the ability of a substance or material to provide biologically inert surfaces which are receptive to the growth of new host bone.

5 The term "osteoinductive" as used herein shall be understood to refer to the ability of a substance to recruit cells from the host which have the potential for repairing bone tissue.

10 Use of the expression "bone-derived elements" shall be understood to refer to pieces of bone in any variety of sizes, thicknesses and configurations including particles, fibers, strips thin to thick sheets, etc., which can be obtained by milling, slicing, cutting or machining whole bone.

15 The expression "surface-exposed collagen" shall be understood to refer to the result obtained by demineralizing the aforementioned bone-derived elements, the demineralization ranging from substantially complete (in which case the bone-derived elements are primarily collagen) to partial or superficial (in which case only
20 the surfaces of the bone-derived elements present exposed collagen). Partial or superficial demineralization produces bone-derived elements having a surface binding region, namely, exposed collagen while retaining a
25 strengthening region, namely, the unaffected mineralized region of the bone-derived elements.

BRIEF DESCRIPTION OF THE DRAWINGS

Various embodiments are described below with reference to the drawings wherein:

5 FIG. 1 is a cross-sectional view of bone from the diaphyseal region which has been sliced longitudinally into several cortical bone sheets;

10 FIG. 2 is an enlarged perspective view of an osteoimplant of the invention possessing sheets of partially demineralized bone at their surface and an interior made up of mineralized or partially demineralized bone;

FIG. 3 is a view of a human femur showing an osteoimplant of the invention, as shown in FIG. 3A, fashioned as a femoral bone replacement;

15 FIG. 4 is a partial view of the human vertebral column showing a disc-shaped osteoimplant of the invention installed at an intervertebral site;

20 FIGS. 5 and 5A are views of a human skull showing an osteoimplant of the invention fashioned as a parietal bone replacement;

FIG. 6 is an enlarged perspective view of an osteoimplant of the invention possessing alternating layers of bone sheets and cubes with channels between the cubes.

25 FIG. 7 is a partial view of the human vertebral column showing installation of the osteoimplant of Fig. 6

at a posterolateral intertransverse process fusion site;
and,

FIG. 8A is an enlarged perspective view of an
osteointerplant of the invention possessing layers of bone
5 sheets bonded together via chemical bonds formed by
catalysis with tissue transglutaminase, as shown in FIG.
8.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The osteointerplant of the present invention comprises
10 a solid aggregate of bone-derived elements having
chemical linkages between their surface-exposed collagen
molecules thus bonding adjacent bone elements to each
other. In order to expose the collagen located on the
outer surface of bone, the bone elements must be at least
15 partially demineralized. Demineralization methods remove
the mineral component of bone employing acid solutions.
Such methods as used by the present invention are well
known in the art, see for example, Reddi et al., *Proc.*
Nat. Acad. Sci. 69, pp1601-1605 (1972), incorporated
20 herein by reference. The strength of the acid solution,
the shape of the bone and the duration of the
demineralization treatment will determine the extent of
demineralization. Reference in this regard may be made to
Lewandrowski et al., *J. Biomed Materials Res*, 31, pp365-
25 372 (1996), also incorporated herein by reference. The
sources for the bone-derived elements herein include

cortical and cancellous bone and are preferably allogenic but also include xenogenic sources such as bovine and porcine bone.

5 When prepared from bone-derived elements that are only superficially demineralized, the osteoimplant herein will tend to possess a fairly high compression strength, e.g., one approaching that of natural bone. Accordingly, when an osteoimplant exhibiting relatively high compression strength is desired, e.g., on the order of
10 from about 10 to about 200 MPa, and preferably from about 20 to about 100 MPa, it is necessary to employ bone-derived elements which retain a high proportion of their original mineral content or, stated another way, which have only been superficially demineralized.

15 In addition to containing bone-derived elements, the osteoimplant of this invention can optionally possess one or more other components such as reinforcing particles, fibers, fillers, bone-growth inducing substances, adhesives, plasticizers, flexibilizing agents, hydration
20 facilitating agents, biostatic/biocidal agents, substances imparting radiopacity, metallic meshes and the like. Examples of reinforcing particles include fully mineralized cortical and cancellous bone, and partially demineralized cortical and cancellous bone in any form,
25 including particles, sheets and shaped bone pieces; graphite or pyrolytic carbon. Examples of fillers

include mineral material such as hydroxyapatite, tricalcium phosphate and other calcium salts, bone powder, fully mineralized and partially or fully demineralized cortical and cancellous bone in any form, including particles such as demineralized bone powder (or "demineralized bone matrix" as it may also be called) sheets and shaped bone pieces, graphite or pyrolytic carbon, bioglass or other bioceramic or natural or synthetic polymers, e.g., bioabsorbable polymers such as polyglycolide, polylactide, glycolide-lactide copolymer, and the like, and nonbioabsorbable materials such as starches, polymethyl methacrylate, polytetrafluoroethylene, polyurethane, polyethylene and nylon. Suitable plasticizers, flexibilizing agents and hydration facilitating agents, include liquid polyhydroxy compounds such as glycerol, monacetin, diacetin, and mixtures thereof. Suitable biostatic/biocidal agents include antibiotics, povidone, sugars, and mixtures thereof; suitable surface agents include the biocompatible nonionic, cationic, anionic and amphoteric surfactants, and mixtures thereof. The osteoimplant can also possess bone-growth inducing substances which include any of a variety of medically and/or surgically useful substances which are described below.

The osteoimplant can possess one or more cavities which, if desired, can communicate with the surface of

the implant through pores, apertures, perforations or channels provided for this purpose and ranging in average diameter from a few microns to several millimeters. Such cavities and their associated pores, apertures, perforations, and channels can be partially or completely filled with one or more medically/surgically useful substances which promote or accelerate new bone growth or bone healing due, e.g., to some osteogenic, osteoconductive and/or osteoconductive effect. Useful substances of this kind which can be incorporated into the osteoimplant of this invention include, e.g., collagen, insoluble collagen derivatives, etc., and soluble solids and/or liquids dissolved therein, e.g., antiviral agents, particularly those effective against HIV and hepatitis; antimicrobials and/or antibiotics such as erythromycin, bacitracin, neomycin, penicillin, polymyxin B, tetracyclines, viomycin, chloromycetin and streptomycins, cefazolin, ampicillin, azactam, tobramycin, clindamycin and gentamicin, etc.; biocidal/biostatic sugars such as dextrose, glucose, etc.; amino acids, peptides, vitamins, inorganic elements, co-factors for protein synthesis; hormones; endocrine tissue or tissue fragments; synthesizers; enzymes such as collagenase, peptidases, oxidases, etc.; polymer cell scaffolds with parenchymal cells; angiogenic drugs and polymeric carriers containing such drugs;

collagen lattices; antigenic agents; cytoskeletal agents; cartilage fragments, living cells such as chondrocytes, bone marrow cells, mesenchymal stem cells, natural extracts, tissue transplants, bone, demineralized bone, autogenous tissues such as blood, serum, soft tissue, bone marrow, etc.; bioadhesives, bone morphogenic proteins (BMPs), transforming growth factor (TGF-beta), insulin-like growth factor (IGF-1); growth hormones such as somatotropin; bone digestors; antitumor agents; immunosuppressants; angiogenic agents such as basic fibroblast growth factor (bFGF); permeation enhancers, e.g., fatty acid esters such as laurate, myristate and stearate monoesters of polyethylene glycol, enamine derivatives, alpha-keto aldehydes, etc.; and, nucleic acids. These and similar medically/surgically useful substances can be incorporated into the osteoimplant of this invention or any of its constituent bone-derived elements or other components during any stage of the assembly of the implant. Suitable methods of incorporation include coating, immersion saturation, packing, etc. The amounts of medically/surgically useful substances utilized can vary widely with optimum levels being readily determined in a specific case by routine experimentation.

Osteoimplants of any desirable size and/or configuration can be provided, e.g., by machining or

other mechanical shaping operations such as press-molding. Computerized modeling of a specific implant followed by computerized control of the shaping of the implant can be used to provide an intricately shaped
5 osteoimplant which is custom-fitted to the intended site of application with great precision.

Where the invention comprises aggregates of elongate bone-derived elements which, in appearance can be described as filaments, fibers, threads, slender or
10 narrow strips, etc., an osteoimplant can be formed from these elements by a variety of methods. For example, forming a solution or slurry in a suitable medium which can comprise the crosslinking agent, and any proportion of the elongate bone-derived elements being partially or
15 fully demineralized, and fully mineralized. This solution can be formed into an osteoimplant of any shape according to the configuration of a mold into which it is poured. The mold is preferably shaped as a bone or section thereof, or as an implant for grafting. Once
20 contained in a mold, the solution of bone-derived elements can be solidified into a solid osteoimplant by known techniques.

It is within the scope of the invention to supplement or increase the shape-retaining and/or
25 mechanical strength characteristics of the osteoimplant, e.g., by the addition of mechanical fasteners such as

pins, screws, dowels, etc., which can be fabricated from natural or synthetic materials and bioabsorbable as well as nonbioabsorbable materials, by the use of laser tissue welding or ultrasonic bonding, and so forth. In those
5 embodiments of the osteoimplant which are assembled from relatively large bone-derived elements such as sheets, such elements can be provided with mechanically interengaging features, e.g., tongue-and-groove or mortise-and-tenon features, which facilitate their
10 assembly into the final product and/or to fix the elements to each other in a more secured fashion.

The osteoimplant herein is intended to be applied at a bone defect site, e.g., one resulting from injury, defect brought about during the course of surgery,
15 infection, malignancy or developmental malformation. The osteoimplant, suitably sized and shaped as required, can be utilized as a graft or replacement in a wide variety of orthopaedic, neurosurgical and oral and maxillofacial surgical procedures such as the repair of simple and
20 compound fractures and non-unions, external and internal fixations, joint reconstructions such as arthrodesis, general arthroplasty, cup arthroplasty of the hip, femoral and humeral head replacement, femoral head surface replacement and total joint replacement, repairs
25 of the vertebral column including spinal fusion and internal fixation, tumor surgery, e.g., deficit filling,

discectomy, laminectomy, excision of spinal cord tumors,
anterior cervical and thoracic operations, repair of
spinal injuries, scoliosis, lordosis and kyphosis
treatments, intermaxillary fixation of fractures,
5 mentoplasty, temporomandibular joint replacement,
alveolar ridge augmentation and reconstruction, onlay
bone grafts, implant placement and revision, sinus lifts,
etc. Specific bones which can be repaired or replaced
with the osteoimplant herein include the ethmoid,
10 frontal, nasal, occipital, parietal, temporal, mandible,
maxilla, zygomatic, cervical vertebra, thoracic vertebra,
lumbar vertebra, sacrum, rib, sternum, clavicle, scapula,
humerus, radius, ulna, carpal bones, metacarpal bones,
phalanges, ilium, ischium, pubis, femur, tibia, fibula,
15 patella, calcaneus, tarsal, and metatarsal bones.

The method of manufacturing the osteoimplant of the
present invention comprises providing a quantity of bone-
derived elements initially presenting surface-exposed
collagen and subsequently forming chemical linkages
20 between the surface-exposed collagen of adjacent bone-
derived elements to bond the elements into a solid
aggregate. These chemical linkages can be formed
employing a variety of known methods including chemical
reaction, the application of energy such as radiant
25 energy, which includes irradiation by UV light or
microwave energy, drying and/or heating and dye-mediated

photo-oxidation; dehydrothermal treatment in which water is slowly removed while the bone tissue is subjected to a vacuum; and, enzymatic treatment to form chemical linkages at any collagen-collagen interface. The preferred method of forming chemical linkages is by chemical reaction.

Chemical crosslinking agents include those that contain bifunctional or multifunctional reactive groups, and which react with functional groups on amino acids such as epsilon-amine functional group of lysine or hydroxy-lysine, or the carboxyl functional groups of aspartic and glutamic acids. By reacting with multiple functional groups on the same or different collagen molecules, the reacting chemical crosslinking agent forms a reinforcing cross-bridge.

Suitable chemical crosslinking agents include: mono- and dialdehydes, including glutaraldehyde and formaldehyde; polyepoxy compounds such as glycerol polyglycidal ethers, polyethylene glycol diglycidal ethers and other polyepoxy and diepoxy glycidal ethers; tanning agents including polyvalent metallic oxides such as titanium dioxide, chromium dioxide, aluminum dioxide, zirconium salt, as well as organic tannins and other phenolic oxides derived from plants; chemicals for esterification of carboxyl groups followed by reaction with hydrazide to form activated acyl azide

functionalities in the collagen; dicyclohexyl
carbodiimide and its derivatives as well as other
heterobifunctional crosslinking agents; hexamethylene
diisocyanate; sugars, including glucose, will also
5 crosslink collagen.

Glutaraldehyde crosslinked biomaterials have a
tendency to over-calcify in the body. In this situation,
should it be deemed necessary, calcification-controlling
agents can be used with aldehyde crosslinking agents.
10 These calcification-controlling agents include: dimethyl
sulfoxide (DMSO), surfactants, diphosphonates, aminooleic
acid, and metallic ions, for example ions of iron and
aluminum. The concentrations of these calcification-
controlling agents can be determined by routine
15 experimentation by those skilled in the art.

Chemical crosslinking involves exposing the
bone-derived elements presenting surface-exposed collagen
to the chemical crosslinking agent, either by placing the
elements in a solution of the chemical crosslinking
20 agent, or by exposing them to the vapors of the chemical
crosslinking agent under conditions appropriate for the
particular type of crosslinking reaction. Such
conditions include: an appropriate pH and temperature,
and for times ranging from minutes to days, depending
25 upon the level of crosslinking desired, and the activity
of the chemical crosslinking agent. The osteoimplant is

then washed to remove all leachable traces of the chemical.

When enzymatic treatment is employed, useful enzymes include those known in the art which are capable of catalyzing crosslinking reactions on proteins or peptides, preferably collagen molecules, e.g., transglutaminase as described in Jurgensen et al., *The Journal of Bone and Joint Surgery*, 79-A (2), 185-193 (1997), herein incorporated by reference.

Formation of chemical linkages can also be accomplished by the application of energy. One way to form chemical linkages by application of energy is to use methods known to form highly reactive oxygen ions generated from atmospheric gas, which in turn, promote oxygen crosslinks between surface-exposed collagen. Such methods include using energy in the form of ultraviolet light, microwave energy and the like. Another method utilizing the application of energy is a process known as dye-mediated photo-oxidation in which a chemical dye under the action of visible light is used to crosslink surface-exposed collagen.

Another method for the formation of chemical linkages is by dehydrothermal treatment which uses combined heat and the slow removal of water, preferably under vacuum, to achieve crosslinking of the bone-derived elements. The process involves chemically combining a

hydroxy group from a functional group of one collagen molecule and a hydrogen ion from a functional group of another collagen molecule reacting to form water which is then removed resulting in the formation of a bond between the collagen molecules.

Referring to the drawings, as shown in FIG. 1, the cortical portion of bone 10 taken from the diaphyseal region is cut into cortical bone sheets 11 of varying width by slicing the bone longitudinally. If desired, cortical bone sheets 11 can be further cut to uniform size and shape, as in bone-derived sheets 21 of the osteoimplant 20 shown in FIG. 2.

FIG. 2 illustrates an osteoimplant 20 comprising cortical bone-derived sheets 21 having a fully or partially demineralized outer surface with surface-exposed collagen, and a nondemineralized or partially demineralized core 22. Alternatively, one or more bone-derived sheets can be made from substantially completely demineralized bone. Also, another component such as demineralized bone powder can be coated on the bone-derived sheets. The entire structure has crosslinked collagen on adjacent bone-derived sheets to provide increased adhesion between them. The total thickness of the osteoimplant will ordinarily be at least about 2 to about 20 mm. Osteoimplant 20 can be cut, machined, and/or otherwise formed into any other desired shape or

dimension for implantation into a body. Thus, as shown in FIG. 3A, a substantially cylindrically shaped osteoimplant 30 can be made for use as a long bone segment replacement 31 for a femur 32 of FIG. 3. To form
5 a cylinder, a substantially square or rectangular osteoimplant can be shaped on a lathe to the required diameter. A cavity can be formed by removing bone material with, for example, a drill, or, alternatively, a cavity can be formed by assembling appropriately
10 configured layers of bone-derived elements.

As shown in FIG. 4, the disc-shaped osteoimplant 40 is shown inserted at the intervertebral fibrocartilage site 41 on the anterior side of vertebral column 42.

In FIG. 5, parietal osteoimplant 50 is sized and
15 shaped to form part of the parietal bone for skull 51 in FIG. 5A.

In FIG. 6, osteoimplant 60 is built up from bone-derived sheet sections 61 of surface demineralized cortical bone, and from bone-derived cube sections 62 of
20 surface demineralized cancellous bone of uniform, square cross section. These sheet and cube constituents are arranged in alternating layers as shown. After assembly, the structure is subjected to treatment for cross-linking. Because of the open structure of osteoimplant
25 60 resulting from the pattern of channels 63, the osteoimplant permits vascular penetration or host bone

ingrowth therein and/or diffusion of one or more medically/surgical useful substances therefrom.

Osteoimplant 60 is shown installed as a spinal onlay graft attached via insertion of the transverse processes
5 71 into channels 63, for posterolateral intertransverse process fusion on vertebral column 70 of FIG. 7.

In FIG. 8A, osteoimplant 80 comprises bone-derived sheets 81 having a fully or partially demineralized outer surface. As shown in FIG. 8, a bone-derived sheet has
10 one side coated with tissue transglutaminase 83 and, the mating surface of the adjacent sheet is coated with CaCl_2 82 solution. As osteoimplant 80 is assembled, contact between the two complimentary sides of bone-derived sheets results in tissue transglutaminase 83 catalyzing
15 collagen crosslinking at the interface of adjacent bone-derived sheets 81.

The following examples are further illustrations of the osteoimplant of this invention.

Example 1

20 A cortical section of bone from the diaphyseal region was cut in the longitudinal direction while continuously wetted with water into approximately 1.5 mm thick sheets using a diamond-bladed saw. The cortical bone-derived sheets were then frozen to -70°C and freeze-
25 dried for 48 hours, and subsequently, were placed into

excess 0.6N HCl solution for 1.5 hours with constant stirring, washed in water for 5 minutes, and soaked for 1.5 hours in BupH phosphate buffered saline. The bone-derived sheets were assembled into a layered structure and held with a clamp. The clamped structure was then placed into a solution of 10% neutral, buffered formalin for 48 hours to crosslink the exposed collagen surfaces. After crosslinking, the clamp was removed, and the structure was placed in a container and allowed to rinse under running water for several hours. The osteoimplant was cut to shape on a band saw, and then placed in an excess aqueous solution of glycerol. After seven hours, the excess solution was removed, and the osteoimplant was freeze-dried.

15

Example 2

Elongate bone-derived fibers were milled from cortical bone, and were fully demineralized in excess 0.6N HCl solution. These fibers were washed with water, and soaked in an aqueous solution of glycerol. Additionally, fully mineralized bone-derived fibers were added to the solution which was stirred and left for 12 hours at room temperature. The solution containing the soaked mineralized and demineralized bone-derived fibers were poured through a 106 micron sieve to recover the fibers. The mixture of mineralized and demineralized fibers was placed in a cylindrical die, and pressure-

25

5 treated to 10,000-50,000 psi in a press for 15 minutes,
and were then heated for 2 to 12 hours at 37-55 degrees
C. The resulting osteoimplant pellet was freeze-dried,
and placed in polyethylene glycol diglycidal ether for 12
hours at room temperature.

Example 3

Bone-derived sheets derived from human cortical
bone, approximately 1 mm thick by 7 mm wide by 50 mm
long, were treated for 10 minutes in 0.6N HCl to expose
10 surface collagen. Bone-derived cubes derived from human
cancellous bone, 10 mm x 10 mm, were treated to expose
surface collagen at the outer borders of the cubes. All
bone-derived sheets and cubes were washed in water. The
pieces were assembled together with bone-derived sheets
15 bordering the cubes, and clamped into place. The
construct was then placed into a solution of 10% neutral
buffered formalin for 3 hours to crosslink the surface-
exposed collagen. The resulting osteoimplant was then
washed in water, and cut to size on a band saw. See Fig.
20 6.

Example 4

Human cortical bone-derived sheets approximately 1
mm thick were surface demineralized for 15 minutes in
0.6N HCl, then washed in running water. Tissue transglu-

taminase was reconstituted to give a 1 mg/ml solution. For each demineralized bone-derived sheet in the construct, the surface was blotted dry, then 40 $\mu\text{l}/\text{cm}^2$ area of the tissue transglutaminase was applied to one side and an equivalent volume of 0.1M CaCl_2 solution was applied to the mating surface of the next demineralized bone-derived sheet. This was repeated sequentially. The resulting osteoimplant was clamped and placed into a humidity chamber to promote crosslinking for approximately 30 minutes, then washed in water.

Example 5

Cortical bone-derived sheets, approximately 2 mm thick, were surface demineralized in 0.6N HCl solution for 1 hour with constant stirring. The bone-derived sheets were then coated with dry, demineralized bone powder having a particle size of 300 microns or less, and assembled into layers. The construct was clamped into place, and placed into a solution of 10% neutral buffered formalin for 12 hours to permit collagen crosslinking. The resulting osteoimplant was washed in water to remove excess chemicals.

WHAT IS CLAIMED IS:

1. An osteoimplant which comprises a solid aggregate of bone-derived elements, adjacent bone-derived elements being bonded to each other through chemical linkages between their surface-exposed collagen.
2. The osteoimplant of Claim 1 wherein the bone-derived elements are superficially demineralized particles, strips or sheets of allogenic, xenogenic cortical and/or cancellous bone.
3. The osteoimplant of Claim 1 wherein the bone-derived elements are substantially completely demineralized particles, strips or sheets of allogenic, xenogenic cortical and/or cancellous bone.
4. The osteoimplant of Claim 1 containing at least one other component.
5. The osteoimplant of Claim 4 wherein the component is selected from the group consisting of reinforcing particle or fiber, filler, bone-growth inducing substance, growth factors, fully mineralized allogenic or xenogenic bone, cellular material, genetic material, calcification-controlling agent, hydration agent, inorganic compounds and polymers.

6. The osteoimplant of Claim 1 possessing a cross section for at least a portion of its length which is, or approximates, a circle, oval or polygon, the implant optionally possessing a cavity for at least a portion of its length.

7. The osteoimplant of Claim 1 configured as a graft.

8. The osteoimplant of Claim 1 configured as a replacement for a bone or section thereof.

9. The osteoimplant of Claim 8 configured as an intervertebral insert, a long bone, a cranial bone, a bone of the pelvis, or a bone of the hand or foot or section thereof.

10. The osteoimplant of Claim 1 wherein the chemical linkages are formed by chemical crosslinking, application of energy, dehydrothermal treatment or enzymatic treatment.

11. The osteoimplant of Claim 1 possessing a compression strength of from about 10 to about 200 MPa.

20

12. The osteoimplant of Claim 1 possessing a compression strength of from about 20 to about 100 MPa.

13. The osteoimplant of Claim 1 possessing a hydration-facilitating agent.

14. The osteoimplant of Claim 1 wherein the hydration-facilitating agent is glycerol.

15. A method for the manufacture of an osteoimplant which comprises:

- 10 a) providing a quantity of bone-derived elements initially presenting surface-exposed collagen; and,
- b) forming chemical linkages between the surface-exposed collagen of adjacent bone-derived
- 15 elements to bond said elements into a solid aggregate.

16. The method of Claim 15 wherein the bone-derived elements are substantially completely demineralized particles, strips or sheets of allogenic and/or xenogenic cortical bone.

17. The method of Claim 15 wherein chemical linkages are formed by chemical crosslinking, application of energy, dehydrothermal treatment, enzymatic treatment or any combination of the foregoing.

5 18. The method of Claim 15 carried out in a mold.

19. The method of Claim 18 wherein the shaping surfaces of the mold are such as to provide an osteoimplant configured as a bone or section thereof.

10 20. The method of Claim 18 wherein the shaping surfaces of the mold are such as to provide an osteoimplant configured as an intervertebral insert, a long bone, a cranial bone, a bone of the pelvis, or a bone of the hand or foot or section thereof.

15 21. The method of Claim 17 wherein chemical linkages are formed by contacting bone-derived elements with a chemical crosslinking agent to form chemical linkages between the surface-exposed collagen of adjacent bone-derived elements.

22. The method of Claim 21 wherein the chemical crosslinking agent is selected from the group consisting of aldehydes, dialdehydes, polyepoxy compounds, polyvalent metallic oxides, organic tannins, phenolic
5 oxides, sugars, dicyclohexyl carbodiimide and hexamethylene diisocyanate.

23. The method of Claim 17 wherein chemical linkages are formed by irradiating the bone-derived elements in a gaseous environment to provide oxygen ions
10 which thereafter react with surface-exposed collagen of adjacent bone-derived elements forming chemical linkages therebetween.

24. The method of Claim 17 wherein linkages are formed by dye-mediated photo-oxidation.

15 25. The method of Claim 17 wherein the dehydrothermal treatment comprises heating the bone-derived elements to remove water therefrom and removing the water.

26. The method of Claim 17 wherein chemical linkages are formed by treating the bone-derived elements with an enzyme which catalyzes formation of chemical linkages between amino acid-functional groups of the surface-exposed collagen of adjacent bone-derived elements.

27. The method of Claim 26 wherein the enzyme is a tissue transglutaminase.




FIG. 1




FIG. 2

SUBSTITUTE SHEET (RULE 26)

2/5




FIG. 3




FIG. 3A




FIG. 4




FIG. 5




FIG. 5A

4/5




FIG. 6




FIG. 7

5/5




FIG. 8A

FIG. 8

INTERNATIONAL SEARCH REPORT

Intern. Appl. No.

PCT/US 99/02560

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61L27/00 A61F2/28

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61L A61F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 96 39203 A (BIOCOLL LAB INC) 12 December 1996 see page 12, line 25 - line 34 see page 16, line 1 - page 17, line 4 see page 18, line 35 - page 19, line 13 see page 22, line 16 see page 34, line 29 - page 35, line 1; claim 11	1-5, 7-10, 13-22
Y	---	6,23-27
Y	WO 98 00183 A (SHAW ROBERT F) 8 January 1998 see page 8, line 7 - line 9 see page 33, line 14 - line 19; claim 18 --- -/--	26,27

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is compared with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

3 June 1999

Date of mailing of the international search report

11/06/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer:

Stach, R

INTERNATIONAL SEARCH REPORT

Intern. Jnal Application No

PCT/US 99/02560

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 4 932 973 A (GENDLER EL) 12 June 1990 cited in the application see column 3, line 55 - line 56; figures ---	6
Y	US 4 623 553 A (RIES PETER ET AL) 18 November 1986 see claim 5 ---	23
Y	EP 0 411 925 A (UNIV NORTH CAROLINA) 6 February 1991 see abstract see page 2, line 20 - line 21 ---	24
Y	EP 0 693 523 A (COL BAR R 6 D LTD) 24 January 1996 see page 3, line 16 - line 24 ---	25
A	EP 0 243 151 A (AJINOMOTO KK) 28 October 1987 see page 3, line 64 - page 4, line 1 -----	26,27

INTERNATIONAL SEARCH REPORT

Information on patent family members

Interr. Application No

PCT/US 99/02560

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9639203 A	12-12-1996	AU 6107496 A CA 2222626 A CN 1192700 A EP 0851772 A	24-12-1996 12-12-1996 09-09-1998 08-07-1998
WO 9800183 A	08-01-1998	US 5853746 A AU 3581597 A CA 2258601 A EP 0912204 A NO 986083 A	29-12-1998 21-01-1998 08-01-1998 06-05-1999 01-03-1999
US 4932973 A	12-06-1990	DE 3435771 A FR 2552659 A GB 2148122 A, B	25-04-1985 05-04-1985 30-05-1985
US 4623553 A	18-11-1986	EP 0164483 A CA 1259266 A JP 1810369 C JP 5022547 B JP 61045768 A	18-12-1985 12-09-1989 27-12-1993 29-03-1993 05-03-1986
EP 0411925 A	06-02-1991	US 5147514 A AU 626442 B AU 6007490 A CA 2022480 A DE 69031483 D DE 69031483 T ES 2109230 T JP 3148293 A US 5854397 A US 5332475 A	15-09-1992 30-07-1992 07-02-1991 03-02-1991 30-10-1997 05-02-1998 16-01-1998 25-06-1991 29-12-1998 26-07-1994
EP 0693523 A	24-01-1996	CA 2154294 A JP 9031334 A	20-01-1996 04-02-1997
EP 0243151 A	28-10-1987	DE 3783073 A JP 2606213 B JP 63152601 A US 5558861 A	28-01-1993 30-04-1997 25-06-1988 24-09-1996